



# Swoosh

## Urethane Floor Sealer

Sellador Uretano

- VOC Compliant • Long Lasting Base Coat
- Protects Porous Floors • High Gloss



### Technical Data Sheet

#### PRODUCT DESCRIPTION:

A high solids, high gloss, VOC compliant, oil modified polyurethane formulated for use on gymnasiums, residential and commercial wood flooring.

#### USES:

For use on wood floors as a sealer, permanent finish and protectorant.

#### ADVANTAGES:

Tough wear properties. Excellent adhesion. Long lasting. Protects wood floors with superior gloss. VOC compliant urethane coating.

#### SPECIFICATIONS:

- Total Solids: 52%
- pH: N/A
- Color: Amber
- Solubility in Water: Insoluble
- Odor: Solvent
- Flash Point: 105° F
- Viscosity: Water Thin Liquid
- Weight per Gallon: 7.45 Lbs.

#### PRODUCT/CONTAINER

#### DISPOSAL:

Dispose of used/unwanted product according to state and local regulations. Offer container for recycling.

#### SIZES AVAILABLE:

5 Gallon Pail



Recyclable packaging

#### DIRECTIONS FOR PRODUCT USE:

**CAUTION:** If the composition or origin of an existing finish is unknown, it is strongly recommended that a test patch be applied to determine compatibility and adequate adhesion characteristics.

**FLOOR PREPARATION:** Sanding is advisable for new floors and old, badly worn floors. After sanding, sweep or vacuum the floor to remove wood dust and dirt and then tack rag the floor using a waterless cleaner.

**SEALED FLOORS IN GOOD CONDITION:** Clean heavily soiled floors thoroughly with a waterless cleaner. Allow the floor to dry, then screen with a 100-120 grit screen disk. Sweep or vacuum the floor to remove wood dust and dirt. Tack rag the floor to remove any fine dirt or dust left from screening.

**APPLYING THE FINISH:** Apply finish only after the floor is thoroughly clean and dry. Apply finish with a lamb's wool applicator, brush or drag/t-bar. Pour finish into an applicator pan if applying with lamb's wool or brush, or a plastic watering can for application with a drag/t-bar. Apply finish in a thin uniform coat. Under warm, low humidity conditions, allow 6-8 hours between coats. Apply no more than 2 coats in 24 hours. Under warm, low humidity conditions, floor may be opened to light traffic after 24-36 hours.

**BUFFING BETWEEN COATS:** Screen between coats with a 120 grit or finer screen to ensure adhesion and to remove raised grains in wood and provide a smoother finished appearance. Sweep or vacuum the floor to remove large quantities of wood and urethane dust. Tack rag floor to remove fine dust. Allow floor to dry thoroughly, then apply the next coat.

Coverage: 500-600 square feet per gallon



It is recommended that protective gloves and safety glasses be worn when using this and all cleaning products. Refer to MSDS for further safety information.



FLOOR COATING AND FINISHING MATERIAL AS TO SLIP RESISTANCE ONLY 210S



#### MANUFACTURED BY:



**AMERICAN** Cleaning Solutions  
Division of American Wax Company, Inc.

39-30 Review Avenue  
Long Island City, New York 11101  
1-888 WAX PLUS • (718) 392-8080 Fax: (718) 482-9366  
Visit us on the web! [www.cleaning-solutions.com](http://www.cleaning-solutions.com)

