

# ZF 33

## Zinc-Free Seal & Finish

Piso Acabado sin Cinc

- High Solids • Wet Look Gloss
- Low V.O.C.
- Environmentally Responsible Ingredients



This product meets Green Seal™ Standard GS-40 based on effective performance and protective limits on VOCs and human & environmental toxicity. GreenSeal.org.



## Technical Data & Training Sheet

### PRODUCT DESCRIPTION:

A high quality, versatile, zinc-free acrylic co-polymer floor finish. Easy to use, easy to repair, good durability and high gloss.

### USES:

Can be used on any floor not affected by water including resilient tile, composition tile and terrazzo.

### ADVANTAGES:

GREEN SEAL™ CERTIFIED under GS-40 standard for industrial and institutional floor-care products. Environmentally responsible finish dries to a high shine without buffing. Non-powdering ZF 33 Zinc-Free Seal & Finish is scuff, scratch and slip resistant and is unaffected by detergents. Resilient surface can be both spray buffed and high speed burnished.

### SPECIFICATIONS:

Solids: 20%  
pH: 8-8.5  
Color: Clear  
Odor: Slight Acrylate  
Flash Point: N/A  
Viscosity: Water thin liquid  
Weight per Gallon: 8.6 Lbs.  
Coverage: 1500 to 2000 sq.ft./gal

### PRODUCT/CONTAINER

#### DISPOSAL:

Dispose of used/unused/unwanted product according to Federal, state & local regulations. Offer container for recycling.

### SIZES AVAILABLE:



Recyclable packaging

### DIRECTIONS FOR PRODUCT USE:



It is recommended that protective gloves and safety glasses be worn when using this and all cleaning products. Respiratory protection is generally not required. No special ventilation is normally required. Refer to SDS for further safety information.



1. Strip all old floor finish or wax with **FOCUS FS 22 Floor Stripper**. Rinse thoroughly and allow floor to dry.



2. Apply 3-4 coats of **ZF 33 Zinc-Free Seal & Finish** with mop or applicator to produce a long lasting and durable shine.



3. Allow 30-45 minutes drying time between coats, depending on ambient humidity.



4. To maintain high gloss, surface can be spray buffed or high speed burnished.